

WB10018-D2 MMA WELDING ELECTRODE

Classifications	AWS A5.5: E10018-D2-H4 R				BS EN ISO 18275: E62 5 MnMo B T 3 2 H5					2 H5
Product Description	All positional, basic coated, low hydrogen, high strength electrode depositing exceptionally clean metal of high radiographic quality. The addition of iron powder gives a recovery of ~ 110%.							der		
Applications	Used for the welding of medium to high tensile strength steels. Widely used for welding pressure vessels, forgings and castings with excellent sub-zero toughness after tempering/post weld heat treatment. Typical grades ASTM A487 2B, AISI 4130, 4140, BS970 709M40 (En19).									
All-Weld Metal Composition										
(Weight %)	С	Mn	Si	S	Р	Мо	Cr	Ni	V	
min.	0.05	1.65	0.15	-	-	0.25	-	0.60	-	
max.	0.15	2.00	0.80	0.025	0.025	0.45	0.20	1.00	0.030	
Typical All-Weld Metal Mechanical Properties	Ultimate Tensile Strength Yield Stress/0.2% Proof Stress Elongation on 5D Impact Energy CV @ -51°C Stress-relieved @ 650°C/6 Hrs			N/mm² N/mm² % Joules						

Electrode Dia. (mm)		1.6mm	2.0mm	2.5mm	3.2mm	4.0mm	5.0mm	6.0mm
Electrode Length (mm)		-	-	350	450	450	450	450
	min.	-	-	60	90	130	160	220
Current Range (Amps)	max.	-	-	100	140	180	220	300
Packaging Information								
Kg Per Packet Approx. Pieces Per Kg Vac Pac Approx. Kg Carton		- -	- -	5 44 6.4	5 21 10.8	5 15 11.4	5 10 11.1	5 7 11.4
Vac Pac Approx. Kg Carton - - 0.4 10.8 11.4 11.1 11.4 Storage and Re-Drying Storage It is recommended that the WB range of electrodes are stored in a dry heated store at a minimum temperature of 18°C, and a maximum relative humidity of 60%. To avoid damage to the coatings no more than 4 cartons should be staked on top of another. Re-drying if standard packaging Re-dry @ 350°C for 2 hours and then transfer to holding oven and hold @ 100 - 200°C, or 50-100°C in heated quiver.								

